

Product KAOLIN OR CHINA CLAY

 Lot #
 3315

 Mfg. Date
 8/2022

 Shelf Life
 5 years

Results
Conforms
12.59 %
0.85 %
Passes test
Passes test
<10 ppm
0



Product KAOLIN OR CHINA CLAY

Lot # 08302123 **Manufacturing Date** 10/2021

Properties	Results	
Moisture %	0.74	
+325 residue	0.45	
GEB	75.3	

Kaolin is not of metallic mercury content.



Product KAOLIN OR CHINA CLAY

Lot # 2697 Shelf Life 5 years

Properties	Results	
Identification	Conforms	
Loss on ignition	12.49 %	
Acid soluble	0.88 %	
Carbonate	Passes test	
Iron	Passes test	
Lead	<10 ppm	
Microbial limit (E. Coli)	0	



Product KAOLIN OR CHINA CLAY

Lot # 2455 Shelf Life 5 years

Properties	Specifications	Results	
Identification	NF/USP	Conforms	
Loss on Ignition	< 15.0 %	< 15.0 %	
Acid Soluble	< 2.0 %	< 2.0 %	
Carbonate	No Effectiveness	Pass test	
Iron	Slight tint max	Pass test	
Lead	< 10 ppm	< 10 ppm	
Total Aerobic Microbial Count	N/A	90 cfu/g	
Total Yeast & Mold Count	N/A	< 10 cfu/g	
Escherichia coli	Absent	0	